

For guidance only



**PRODUCT SPECIFICATION**

**IDEM SUPERIOR SHEETS**

<b>GRADE</b>	<b>CB 70</b>
--------------	--------------

<b>COPY COLOUR</b>	<b>BLACK</b>
--------------------	--------------

PROPERTY	METHOD	UNITS	RANGE		
			MIN	TARGET	MAX
GRAMMAGE	ISO 536 - 1995	gm <sup>-2</sup>	70.0	-	76.0
THICKNESS	ISO 534 - 1988	µm	90	94	98
ROUGHNESS - BASE SIDE	ISO 8791 (Part 2) - 1990	ml min <sup>-1</sup>	100	150	350
ROUGHNESS - CB SIDE	ISO 8791 (Part 2) - 1990	ml min <sup>-1</sup>	200	400	600
STIFFNESS – MD	ISO 2493 – 1992	mN	65	80	95
STIFFNESS – XD	ISO 2493 – 1992	mN	30	40	50
TENSILE STRENGTH – MD	ISO 1924 (Part 1) - 1992	N/15 mm	45	-	-
TENSILE STRENGTH – XD	ISO 1924 (Part 1) - 1992	N/15 mm	15	-	-
RELATIVE HUMIDITY	CPOTM 2:27	%	30	37.5	45
DIMENSIONAL STAB. – MD	ISO 8226 (Part 1) - 1985	%	-	-	0.2
DIMENSIONAL STAB. – XD	ISO 8226 (Part 1) - 1985	%	-	-	0.6
50 % RH CURL – CB/BASE	CPOTM 2:12	mm	5	0	5
IMAGE INTENSITY	CPOTM 2:54	% Refl.	33	38	44
OPACITY	CPOTM 2:21	% Refl.	88	91	-
BRIGHTNESS	ISO 2470	% Refl	99	103	107

<b>ISSUE NR. 9</b>	<b>PAGE 1 OF 1</b>	<b>DATE : 03/03/2010</b>
Authorisation	Director Customer Technical Services	P. Marneffer 